



## Basic Quality Statistical Summary Report

**Period** 01/01/2011 - 11/01/2011  
**Plant** 474-Denniston 58-009  
**Product** 2072-Class II Limestone Sand  
**Specification** Class II Limestone Sand

Sieve/Test	Tests	Average	Target	Specification
3" (75mm)	3	100.0		100
2 1/2" (63mm)	3	100.0		
2" (50mm)	3	100.0		
1 1/2" (37.5mm)	3	100.0		
1" (25mm)	3	100.0		60-100
3/4" (19mm)	3	100.0		
1/2" (12.5mm)	3	100.0		
3/8" (9.5mm)	3	100.0		
#4 (4.75mm)	3	88.3		
#8 (2.36mm)	3	58.3		
#16 (1.18mm)	3	31.0		
#30 (0.6mm)	3	17.4		
#50 (0.3mm)	3	9.9		
#100 (0.15mm)	3	7.6		0-30
#200 (75um)	3	7.03		
Pan	3	0.00		
FM	3	3.87		
Wash Loss (#200/75um)	3	6.9		0-7
Total Moisture	3	6.53		