



Basic Quality Statistical Summary Report

Plant 474-Denniston 58-009
Product 2121-MDOT 21AA Spec.
Specification MDOT 21AA Spec. Production

Sieve/Test	Tests	Average	Target	Specification
1 1/2" (37.5mm)	1	100		100-100
1" (25mm)	1	98		85-100
3/4" (19mm)	1	89		
1/2" (12.5mm)	1	70		50-75
3/8" (9.5mm)	1	60		
#4 (4.75mm)	1	44		
#8 (2.36mm)	1	31		20-45
PAN (0um)	1	0		
Absorption	1	3.22		
FM	1	5.76		
LA Abrasion Small (B,500)	1	39		
Proc-Mod Max Dry Density	1	134.0		
Proc-Mod Opt Moisture	1	6.1		
Proc-Std Max Dry Density	1	130.9		
Proc-Std Opt Moisture	1	6.3		
SPGR (Apparent,Gsa)	1	2.772		
SPGR (Dry,Gsb)	1	2.545		
SPGR (SSD)	1	2.627		
Total Moisture	1	5.15		
Unit Wt (Rodded)	1	112.6		
Unit Wt SSD (Rodded)	1	116.2		
Voids (Rodded)	1	29.0		
Wash Loss (#200/75um)	1	6.8		4-10