



## Basic Quality Statistical Summary Report

**Period** 01/01/2011 - 11/01/2011  
**Plant** 474-Denniston 58-009  
**Product** 2026-MDOT 26A  
**Specification** MDOT 26A Production

Sieve/Test	Tests	Average	Target	Specification
3/4" (19mm)	70	100		100-100
1/2" (12.5mm)	70	97		95-100
3/8" (9.5mm)	70	71		60-90
#4 (4.75mm)	70	7		5-30
#8 (2.36mm)	70	3		0-12
#16 (1.18mm)	4	2		
#30 (0.6mm)	4	2		
#50 (0.3mm)	4	2		
#100 (0.15mm)	4	2		
#200 (75um)	4	2		
Pan	70	0		
FM	70	6.18		
Wash Loss (#200/75um)	70	1.7		0-3
Total Moisture	68	4.91		
Absorption	13	3.39		
SPGR (Dry,Gsb)	13	2.550		
SPGR (SSD)	13	2.637		
SPGR (Apparent,Gsa)	13	2.791		
Shale	23	0.2		
Chert	23	0.0		