



Basic Quality Statistical Summary Report

Period 01/01/2011 - 11/01/2011
Plant 474-Denniston 58-009
Product 2006-MDOT 6AA /ODOT57
Specification MDOT 6AA Production

| Sieve/Test | Tests | Average | Target | Specification |
|-----------------------|-------|---------|--------|---------------|
| 1 1/2" (37.5mm) | 148 | 100 | | 100-100 |
| 1" (25mm) | 147 | 99 | | 95-100 |
| 3/4" (19mm) | 148 | 79 | | |
| 1/2" (12.5mm) | 148 | 43 | | 30-60 |
| 3/8" (9.5mm) | 148 | 25 | | |
| #4 (4.75mm) | 148 | 5 | | 0-8 |
| #8 (2.36mm) | 148 | 2 | | |
| #200 (75um) | 2 | 1 | | |
| Pan | 147 | 0 | | |
| FM | 148 | 6.89 | | |
| Wash Loss (#200/75um) | 147 | 1.4 | | 0-2 |
| Total Moisture | 130 | 4.74 | | |
| Absorption | 40 | 3.00 | | |
| SPGR (Dry,Gsb) | 40 | 2.567 | | |
| SPGR (SSD) | 40 | 2.644 | | |
| SPGR (Apparent,Gsa) | 40 | 2.781 | | |
| Shale | 113 | 0.1 | | |
| Chert | 114 | 0.0 | | |