

Oldcastle Materials

Basic Quality Statistical Summary Report

Plant 465-Offsite
Product 2270-MDOT Class II Sand
Specification MDOT Class II Sand Production

Sieve/Test	Tests	Average	Target	Specification
3" (75mm)	6	100.0		100-100
1" (25mm)	6	100.0		85-100
3/4" (19mm)	6	100.0		
1/2" (12.5mm)	6	100.0		
3/8" (9.5mm)	6	100.0		
1/4" (6.3mm)	6	100.0		
#4 (4.75mm)	6	99.9		
#8 (2.36mm)	6	99.9		
#10 (2mm)	6	99.9		
#16 (1.18mm)	6	99.6		
#20 (0.85mm)	6	99.5		
#30 (0.6mm)	6	97.3		
#40 (0.425mm)	6	97.0		
#50 (0.3mm)	6	83.1		
#60 (0.25mm)	6	82.2		
#100 (0.15mm)	6	44.5		0-30
#200 (75um)	6	9.05		
PAN (0um)	6	0.00		
FM	6	1.92		
Total Moisture	1	7.88		
Wash Loss (#200/75um)	6	6.2		0-7