



Basic Quality Statistical Summary Report

Period 01/01/2011 - 11/01/2011
Plant 469-Maybee 58-004
Product 2002-MI 1" X 3" LIMESTONE
Specification MI 1"X3" LIMESTONE Shipping

Sieve/Test	Tests	Average	Target	Specification
3" (75mm)	3	98		
2 1/2" (63mm)	3	69		
2" (50mm)	3	37		
1 1/2" (37.5mm)	3	15		
1" (25mm)	3	4		
3/4" (19mm)	3	2		
1/2" (12.5mm)	1	3		
3/8" (9.5mm)	1	3		
#4 (4.75mm)	1	3		
#8 (2.36mm)	1	3		
#16 (1.18mm)	1	3		
#30 (0.6mm)	1	3		
#50 (0.3mm)	1	3		
#100 (0.15mm)	1	3		
Pan	3	0		
Wash Loss (#200/75um)	2	1.6		
Total Moisture	2	2.49		
Absorption	1	2.59		
SPGR (Dry,Gsb)	1	2.557		
SPGR (SSD)	1	2.624		
SPGR (Apparent,Gsa)	1	2.739		
Unit Wt (Rodded)	1	90.3		
Unit Wt SSD (Rodded)	1	92.6		
Voids (Rodded)	1	43.3		
LA Abrasion (3,1000)	1	50.0		