



Basic Quality Statistical Summary Report

Plant 469-Maybee 58-004
Product 2010-MI 3/8" SCREENINGS
Specification MI 3/8" SCREENINGS

Sieve/Test	Tests	Average	Target	Specification
3/8" (9.5mm)	1	100		100-100
#4 (4.75mm)	1	78		90-100
#8 (2.36mm)	1	54		60-90
#16 (1.18mm)	1	45		45-70
#30 (0.6mm)	1	39		35-65
#50 (0.3mm)	1	33		25-45
#100 (0.15mm)	1	27		15-35
#200 (75um)	1	23		
PAN (0um)	1	0		
Absorption	1	3.36		
FM	1	3.24		
LA Abrasion Small (D,500)	1	38.0		
SPGR (Apparent,Gsa)	1	2.756		
SPGR (Dry,Gsb)	1	2.522		
SPGR (SSD)	1	2.607		
Total Moisture	1	6.80		
Unit Wt (Rodded)	1	117.3		
Unit Wt SSD (Rodded)	1	121.2		
Voids (Rodded)	1	25.4		
Wash Loss (#200/75um)	1	22.5	15-28	10-30