



# Basic Quality Statistical Summary Report

**Period** 01/01/2011 - 11/01/2011  
**Plant** 469-Maybee 58-004  
**Product** 2021-MI 21AA COMM  
**Specification** MI 21AA COMM

Sieve/Test	Tests	Average	Target	Specification
1 1/2" (37.5mm)	7	100	100-100	100-100
1" (25mm)	7	88	85-100	
3/4" (19mm)	7	75		
1/2" (12.5mm)	7	61	50-75	
3/8" (9.5mm)	7	53		
#4 (4.75mm)	7	41		
#8 (2.36mm)	7	34	20-45	
Pan	7	0		
FM	7	5.96		
Wash Loss (#200/75um)	7	15.0	4-15	
Total Moisture	7	7.18		
Absorption	1	3.53		
SPGR (Dry,Gsb)	1	2.468		
SPGR (SSD)	1	2.555		
SPGR (Apparent,Gsa)	1	2.704		
LA Abrasion (A,500)	1	49.8		
Unit Wt (Rodded)	1	107.4		
Unit Wt SSD (Rodded)	1	111.1		
Voids (Rodded)	1	30.2		