



Basic Quality Statistical Summary Report

Period 01/01/2011 - 11/01/2011
Plant 469-Maybee 58-004
Product 2023-MDOT 23A
Specification MDOT 23A Production

Sieve/Test	Tests	Average	Target	Specification
1" (25mm)	26	100		100-100
3/4" (19mm)	26	92		
1/2" (12.5mm)	26	72		
3/8" (9.5mm)	26	60		60-85
#4 (4.75mm)	26	40		
#8 (2.36mm)	26	29		25-60
#16 (1.18mm)	3	19		
#30 (0.6mm)	3	17		
#50 (0.3mm)	3	16		
#100 (0.15mm)	3	13		
#200 (75um)	3	12		
Pan	26	0		
FM	26	5.71		
Wash Loss (#200/75um)	26	12.3	11-16	9-16
Total Moisture	21	5.46		
Absorption	1	3.24		
SPGR (Dry,Gsb)	1	2.485		
SPGR (SSD)	1	2.565		
SPGR (Apparent,Gsa)	1	2.702		
LA Abrasion (B,500)	1	47.5		
Unit Wt (Rodded)	1	108.7		
Unit Wt SSD (Rodded)	1	112.3		
Voids (Rodded)	1	29.8		