



Basic Quality Statistical Summary Report

Period 01/01/2011 - 11/01/2011
Plant 469-Maybee 58-004
Product 2050-MDOT 5G
Specification MDOT 5G Production

Sieve/Test	Tests	Average	Target	Specification
1 1/2" (37.5mm)	16	100		100-100
1" (25mm)	16	39		
3/4" (19mm)	16	9		
1/2" (12.5mm)	16	4		0-90
3/8" (9.5mm)	16	4		
#4 (4.75mm)	16	3		0-8
#8 (2.36mm)	16	3		
#16 (1.18mm)	1	2		
#30 (0.6mm)	1	2		
#50 (0.3mm)	1	2		
#100 (0.15mm)	1	2		
#200 (75um)	1	2		
Pan	16	0		
FM	16	7.80		
Wash Loss (#200/75um)	16	2.2	1-3	0-3
Total Moisture	14	3.09		
Absorption	1	3.27		
SPGR (Dry,Gsb)	1	2.485		
SPGR (SSD)	1	2.566		
SPGR (Apparent,Gsa)	1	2.705		
LA Abrasion (3,1000)	1	49.1		