



Basic Quality Statistical Summary Report

Period 01/01/2011 - 11/01/2011
Plant 469-Maybee 58-004
Product 2106-MI 6AA Commercial
Specification MI 6AA Commercial

Sieve/Test	Tests	Average	Target	Specification
1 1/2" (37.5mm)	37	100		100-100
1" (25mm)	37	98		
3/4" (19mm)	37	77		
1/2" (12.5mm)	37	36		
3/8" (9.5mm)	37	17		
#4 (4.75mm)	37	5		
#8 (2.36mm)	37	3		
Pan	37	0		
FM	37	6.98		
Wash Loss (#200/75um)	37	1.7		0-3
Total Moisture	29	4.23		
Absorption	1	2.85		
SPGR (Dry,Gsb)	1	2.507		
SPGR (SSD)	1	2.579		
SPGR (Apparent,Gsa)	1	2.700		
LA Abrasion (B,500)	1	47.8		
Unit Wt (Rodded)	1	95.7		
Unit Wt SSD (Rodded)	1	98.5		
Voids (Rodded)	1	38.7		