



# Basic Quality Statistical Summary Report

**Period** 01/01/2011 - 11/01/2011  
**Plant** 469-Maybee 58-004  
**Product** 2110-MDOT FA II  
**Specification** MDOT FA II Production

Sieve/Test	Tests	Average	Target	Specification
3/8" (9.5mm)	62	100.0		100-100
#4 (4.75mm)	62	98.5		90-100
#8 (2.36mm)	62	79.5		65-90
#16 (1.18mm)	62	54.1		45-70
#30 (0.6mm)	62	38.8		30-50
#50 (0.3mm)	62	26.8		18-30
#100 (0.15mm)	62	16.9		10-21
#200 (75um)	61	11.72		
Pan	62	0.00		
FM	62	2.85		
Wash Loss (#200/75um)	62	11.2	8-15	5-15
Total Moisture	48	9.85		
FAA, Us	1	48.2		
Absorption	1	4.98		
SPGR (Dry,Gsb)	1	2.457		
SPGR (SSD)	1	2.579		
SPGR (Apparent,Gsa)	1	2.799		
LA Abrasion (D,500)	2	46.1		
Unit Wt (Rodded)	1	109.9		
Unit Wt SSD (Rodded)	1	115.4		
Voids (Rodded)	1	28.2		
Opt Moisture (Proctor-Mod)	1	5.8		
Max Dry Density (Proctor-Mod)	1	129.0		
Max Dry Density (Proctor-Std)	1	123.5		
Opt Moisture (Proctor-Std)	1	5.0		
FAA, MI	1	5		