



Basic Quality Statistical Summary Report

Period 01/01/2011 - 11/01/2011
Plant 469-Maybee 58-004
Product 2025-MI 25A
Specification MI 25A Production

Sieve/Test	Tests	Average	Target	Specification
3/4" (19mm)	17	100		100-100
1/2" (12.5mm)	17	98		95-100
3/8" (9.5mm)	17	71		60-90
#4 (4.75mm)	17	12		5-30
#8 (2.36mm)	17	7		0-12
#16 (1.18mm)	4	6		
#30 (0.6mm)	4	6		
#50 (0.3mm)	4	5		
#100 (0.15mm)	4	5		
#200 (75um)	4	4		
Pan	17	0		
FM	17	6.05		
Wash Loss (#200/75um)	17	3.7	1-3	0-3
Total Moisture	13	3.84		
Absorption	1	3.14		
SPGR (Dry,Gsb)	1	2.611		
SPGR (SSD)	1	2.693		
SPGR (Apparent,Gsa)	1	2.844		
LA Abrasion (C,500)	1	48.0		
Unit Wt (Rodded)	1	93.0		
Unit Wt SSD (Rodded)	1	95.9		
Voids (Rodded)	1	42.8		