



Basic Quality Statistical Summary Report

Period 01/01/2011 - 11/01/2011
Plant 469-Maybee 58-004
Product 2009-MODIFIED 9
Specification Modified 9 Production

Sieve/Test	Tests	Average	Target	Specification
3/8" (9.5mm)	18	100		100-100
1/4" (6.3mm)	13	91		
#4 (4.75mm)	18	66		30-80
#8 (2.36mm)	18	29		10-40
#16 (1.18mm)	18	18		5-20
#30 (0.6mm)	18	14		
#50 (0.3mm)	18	13		0-13
#100 (0.15mm)	18	11		
#200 (75um)	18	9		
Pan	18	0		
FM	18	4.50		
Wash Loss (#200/75um)	18	9.0		
Total Moisture	14	4.26		
Absorption	1	3.84		
SPGR (Dry,Gsb)	1	2.502		
SPGR (SSD)	1	2.598		
SPGR (Apparent,Gsa)	1	2.768		
LA Abrasion (D,500)	1	34.6		
Unit Wt (Rodded)	1	102.4		
Unit Wt SSD (Rodded)	1	106.3		
Voids (Rodded)	1	34.3		