



Basic Quality Statistical Summary Report

Period 01/01/2011 - 11/01/2011
Plant 471-Newport 58-011
Product 2053-1/2 X 3/8 Black
Specification 1/2 x 3/8 Black Production

Sieve/Test	Tests	Average	Target	Specification
3/4" (19mm)	18	100.0		100-100
1/2" (12.5mm)	33	93.1		90-100
3/8" (9.5mm)	33	43.5		20-50
#4 (4.75mm)	33	2.6		
#8 (2.36mm)	33	1.6		
#16 (1.18mm)	33	1.2		
#30 (0.6mm)	33	1.1		
#50 (0.3mm)	33	1.0		
#100 (0.15mm)	33	0.9		
#200 (75um)	33	0.82		
Pan	33	0.00		
FM	33	6.48		
Wash Loss (#200/75um)	33	0.7		0-2
Total Moisture	14	3.02		
Absorption	1	2.59		
SPGR (Dry,Gsb)	1	2.566		
SPGR (SSD)	1	2.632		
SPGR (Apparent,Gsa)	1	2.749		
LA Abrasion (C,500)	1	32.7		
Unit Wt (Rodded)	1	93.4		
Unit Wt SSD (Rodded)	1	95.8		
Voids (Rodded)	1	41.6		