



# Basic Quality Statistical Summary Report

**Period** 01/01/2011 - 11/01/2011  
**Plant** 471-Newport 58-011  
**Product** 2017-MDOT 17A  
**Specification** MDOT 17A Production

Sieve/Test	Tests	Average	Target	Specification
1" (25mm)	114	100.0		100-100
3/4" (19mm)	114	97.8		90-100
1/2" (12.5mm)	114	57.9		50-75
3/8" (9.5mm)	114	31.2		
#4 (4.75mm)	114	4.7		0-8
#8 (2.36mm)	114	2.0		
Pan	114	0.00		
FM	114	6.64		
Wash Loss (#200/75um)	111	1.0		0-2
Total Moisture	1	4.57		
Absorption	15	2.96		
SPGR (Dry,Gsb)	15	2.561		
SPGR (SSD)	15	2.637		
SPGR (Apparent,Gsa)	15	2.771		
LA Abrasion (C,500)	1	24.2		
Unit Wt (Rodded)	1	97.3		
Unit Wt SSD (Rodded)	1	99.9		
Voids (Rodded)	1	39.5		
Shale	55	0.1		
Chert	54	0.0		