



Basic Quality Statistical Summary Report

Period 01/01/2011 - 11/01/2011
Plant 471-Newport 58-011
Product 2006-MDOT 6AA
Specification MDOT 6AA Production

Sieve/Test	Tests	Average	Target	Specification
1 1/2" (37.5mm)	177	100.0		100-100
1" (25mm)	177	99.1		95-100
3/4" (19mm)	177	78.1		
1/2" (12.5mm)	177	42.8		30-60
3/8" (9.5mm)	177	24.8		
#4 (4.75mm)	177	4.0		0-8
#8 (2.36mm)	177	1.8		
Pan	177	0.00		
FM	177	6.91		
Wash Loss (#200/75um)	173	0.9		0-2
Total Moisture	1	4.93		
Absorption	22	2.88		
SPGR (Dry,Gsb)	22	2.563		
SPGR (SSD)	22	2.636		
SPGR (Apparent,Gsa)	22	2.767		
LA Abrasion (B,500)	1	32.0		
Unit Wt (Rodded)	1	92.0		
Unit Wt SSD (Rodded)	1	94.1		
Voids (Rodded)	1	43.2		
Shale	65	0.2		
Chert	65	0.0		