



Basic Quality Statistical Summary Report

Period 01/01/2011 - 11/01/2011
Plant 468-Ottawa Lake 58-003
Product 2010-MI 3/8" SCREENINGS
Specification 3/8" Screenings Production

Sieve/Test	Tests	Average	Target	Specification
3/8" (9.5mm)	60	100.0	95-100	100-100
1/4" (6.3mm)	46	99.8		
#4 (4.75mm)	69	86.6		
#8 (2.36mm)	69	41.2		
#10 (2mm)	1	23.9		
#16 (1.18mm)	69	21.7		
#30 (0.6mm)	69	15.0		
#40 (0.425mm)	1	18.0		
#50 (0.3mm)	69	11.7		
#100 (0.15mm)	69	10.1		
#200 (75um)	69	9.23		
Pan	69	0.00		
FAA, MI	1	5.1		
FM	69	4.14		
Wash Loss (#200/75um)	69	9.0		0-20
Total Moisture	64	3.0		
Coarseness Factor	60	0.0		
Workability Factor	69	41.2		
FAA, Us	1	48.3		
Absorption	1	2.95		
SPGR (Dry,Gsb)	1	2.595		
SPGR (SSD)	1	2.671		
SPGR (Apparent,Gsa)	1	2.810		
LA Abrasion (D,500)	1	34.6		
Unit Wt (Rodded)	1	96.6		
Unit Wt SSD (Rodded)	1	99.5		
Voids (Rodded)	1	40.2		
Max Dry Density (Proctor-Mod)	1	127.3		
Opt Moisture (Proctor-Mod)	1	6.6		
Max Dry Density (Proctor-Std)	1	122.3		
Opt Moisture (Proctor-Std)	1	5.5		