



Basic Quality Statistical Summary Report

Period 01/01/2011 - 11/01/2011
Plant 468-Ottawa Lake 58-003
Product 2100-AG LIME
Specification

Sieve/Test	Tests	Average	Target	Specification
3/8" (9.5mm)	90	100.0		
#4 (4.75mm)	93	99.6		
#8 (2.36mm)	93	90.0		
#16 (1.18mm)	93	66.9		
#30 (0.6mm)	93	48.4		
#50 (0.3mm)	93	35.7		
#100 (0.15mm)	93	28.2		
#200 (75um)	93	24.1		
Pan	91	0.0		
FM	93	2.31		
Wash Loss (#200/75um)	93	23.4		
Total Moisture	90	4.8		
Absorption	1	1.50		
SPGR (Dry,Gsb)	1	2.667		
SPGR (SSD)	1	2.697		
SPGR (Apparent,Gsa)	1	2.749		
SPGR-CA (Dry)	1	2.749		
Unit Wt (Rodded)	1	114.2		
Unit Wt SSD (Rodded)	1	115.9		
Voids (Rodded)	1	31.2		