



Basic Quality Statistical Summary Report

Period 01/01/2011 - 11/01/2011
Plant 468-Ottawa Lake 58-003
Product 2017-MDOT 17A
Specification 17A Production

Sieve/Test	Tests	Average	Target	Specification
1" (25mm)	95	100.0		100-100
3/4" (19mm)	95	93.1		90-100
1/2" (12.5mm)	95	58.9		50-75
3/8" (9.5mm)	95	33.4		
#4 (4.75mm)	95	5.1		0-8
#8 (2.36mm)	95	2.9		
Pan	95	0.00		
FM	95	6.65		
Wash Loss (#200/75um)	95	1.7		0-2
Total Moisture	82	2.5		
Coarseness Factor	95	68.6		
Workability Factor	95	2.9		
Absorption	24	2.01		
SPGR (Dry,Gsb)	24	2.641		
SPGR (SSD)	24	2.694		
SPGR (Apparent,Gsa)	24	2.788		
LA Abrasion (B,500)	1	28.3		
Unit Wt (Rodded)	1	98.8		
Unit Wt SSD (Rodded)	1	100.9		
Voids (Rodded)	1	39.7		
Shale	7	0.0		
Chert	7	0.0		