



## Basic Quality Statistical Summary Report

**Period** 01/01/2011 - 11/01/2011  
**Plant** 468-Ottawa Lake 58-003  
**Product** 2121-MDOT 21AA  
**Specification** MDOT 21AA Production

Sieve/Test	Tests	Average	Target	Specification
1 1/2" (37.5mm)	65	100.0		100-100
1" (25mm)	65	91.1		85-100
3/4" (19mm)	65	79.4		
1/2" (12.5mm)	65	63.0		50-75
3/8" (9.5mm)	65	51.7		
#4 (4.75mm)	65	35.0		
#8 (2.36mm)	65	23.9		20-45
#16 (1.18mm)	64	16.3		
#30 (0.6mm)	64	13.2		
#50 (0.3mm)	64	11.3		
#100 (0.15mm)	64	10.0		
#200 (75um)	64	9.3		
Pan	65	0.0		
FM	65	5.60		
Wash Loss (#200/75um)	65	9.1		4-10
Total Moisture	49	4.1		
Coarseness Factor	65	63.3		
Workability Factor	65	23.9		
Absorption	1	1.89		
SPGR (Dry,Gsb)	1	2.634		
SPGR (SSD)	1	2.684		
SPGR (Apparent,Gsa)	1	2.773		
LA Abrasion (A,500)	1	31.6		
Unit Wt (Rodded)	1	115.4		
Unit Wt SSD (Rodded)	1	117.6		
Voids (Rodded)	1	29.7		
Max Dry Density (Proctor-Mod)	1	142.6		
Opt Moisture (Proctor-Mod)	1	5.8		
Max Dry Density (Proctor-Std)	1	132.9		
Opt Moisture (Proctor-Std)	1	5.3		