



Basic Quality Statistical Summary Report

Period 01/01/2011 - 11/01/2011
Plant 468-Ottawa Lake 58-003
Product 2023-MDOT 23A
Specification MDOT 23A Production

Sieve/Test	Tests	Average	Target	Specification
1" (25mm)	74	100.0		100-100
3/4" (19mm)	74	97.4		
1/2" (12.5mm)	74	83.3		
3/8" (9.5mm)	74	71.8		60-85
#4 (4.75mm)	74	49.3		
#8 (2.36mm)	74	33.8		25-60
#16 (1.18mm)	70	24.4		
#30 (0.6mm)	70	19.3		
#50 (0.3mm)	70	16.3		
#100 (0.15mm)	70	14.4		
#200 (75um)	70	13.2		9-16
Pan	74	0.0		
FM	74	4.77		
Wash Loss (#200/75um)	74	13.0		9-16
Total Moisture	52	4.3		
Coarseness Factor	74	42.2		
Workability Factor	74	33.8		
Absorption	1	2.02		
SPGR (Dry,Gsb)	1	2.640		
SPGR (SSD)	1	2.694		
SPGR (Apparent,Gsa)	1	2.789		
LA Abrasion (B,500)	1	33.5		
Unit Wt (Rodded)	1	116.2		
Unit Wt SSD (Rodded)	1	118.6		
Voids (Rodded)	1	29.3		
Max Dry Density (Proctor-Mod)	1	142.2		
Opt Moisture (Proctor-Mod)	1	5.7		
Max Dry Density (Proctor-Std)	1	133.8		
Opt Moisture (Proctor-Std)	1	5.5		