



Basic Quality Statistical Summary Report

Period 01/01/2011 - 11/01/2011
Plant 468-Ottawa Lake 58-003
Product 2026-MDOT 26A
Specification MDOT 26A Production

Sieve/Test	Tests	Average	Target	Specification
3/4" (19mm)	109	100.0		100-100
1/2" (12.5mm)	109	99.5		95-100
3/8" (9.5mm)	109	86.2		60-90
#4 (4.75mm)	109	9.9		5-30
#8 (2.36mm)	109	4.2		0-12
#16 (1.18mm)	109	3.2		
#30 (0.6mm)	109	2.8		
#50 (0.3mm)	109	2.6		
#100 (0.15mm)	109	2.5		
#200 (75um)	109	2.4		
Pan	109	0.0		
FM	109	5.88		
Wash Loss (#200/75um)	109	2.2		0-3
Total Moisture	73	2.5		
Coarseness Factor	109	14.4		
Workability Factor	109	4.2		
Absorption	13	2.32		
SPGR (Dry,Gsb)	13	2.623		
SPGR (SSD)	13	2.684		
SPGR (Apparent,Gsa)	13	2.793		
LA Abrasion (C,500)	2	31.0		
Unit Wt (Rodded)	2	95.4		
Unit Wt SSD (Rodded)	2	97.7		
Voids (Rodded)	2	41.5		
Chert	4	0.0		
Shale	4	0.1		