



## Basic Quality Statistical Summary Report

**Period** 01/01/2011 - 11/01/2011  
**Plant** 468-Ottawa Lake 58-003  
**Product** 2029-MDOT 29A  
**Specification** MIDOT 29 A Production

| Sieve/Test            | Tests | Average | Target | Specification |
|-----------------------|-------|---------|--------|---------------|
| 3/4" (19mm)           | 24    | 100.0   |        |               |
| 1/2" (12.5mm)         | 24    | 100.0   |        | 100-100       |
| 3/8" (9.5mm)          | 24    | 96.6    |        | 90-100        |
| #4 (4.75mm)           | 24    | 13.4    |        | 10-30         |
| #8 (2.36mm)           | 24    | 4.8     |        |               |
| #16 (1.18mm)          | 24    | 3.4     |        | 0-10          |
| Pan                   | 24    | 0.0     |        |               |
| Grad Loss             | 23    | 0.000   |        |               |
| Wash Loss (#200/75um) | 24    | 2.5     |        | 0-3           |
| Total Moisture        | 18    | 3.5     |        |               |
| Absorption            | 2     | 2.38    |        |               |
| SPGR (Dry,Gsb)        | 2     | 2.622   |        |               |
| SPGR (SSD)            | 2     | 2.684   |        |               |
| SPGR (Apparent,Gsa)   | 2     | 2.797   |        |               |
| LA Abrasion (D,500)   | 1     | 29.0    |        |               |
| Unit Wt (Rodded)      | 1     | 91.9    |        |               |
| Unit Wt SSD (Rodded)  | 1     | 94.1    |        |               |
| Voids (Rodded)        | 1     | 43.7    |        |               |
| Elongated (3:1)       | 1     | 0.0     |        |               |
| Elongated (5:1)       | 1     | 0.0     |        |               |
| Flat (3:1)            | 1     | 0.0     |        |               |
| Flat (5:1)            | 1     | 0.0     |        |               |
| Flat/Elongated (3:1)  | 1     | 8.0     |        |               |
| Flat/Elongated (5:1)  | 1     | 1.0     |        |               |