



## Basic Quality Statistical Summary Report

**Period** 01/01/2011 - 11/01/2011  
**Plant** 468-Ottawa Lake 58-003  
**Product** 2040-MDOT 4G  
**Specification** MDOT 4G Production

Sieve/Test	Tests	Average	Target	Specification
1 1/2" (37.5mm)	8	100.0		100-100
1" (25mm)	8	89.8		85-100
3/4" (19mm)	8	78.0		
1/2" (12.5mm)	8	59.7		45-65
3/8" (9.5mm)	8	48.1		
#4 (4.75mm)	8	31.5		
#8 (2.36mm)	8	16.7		15-30
#16 (1.18mm)	8	10.6		
#30 (0.6mm)	8	7.8		6-18
#50 (0.3mm)	8	6.5		
#100 (0.15mm)	8	5.7		
#200 (75um)	8	5.3		
Pan	8	0.0		
FM	8	5.95		
Wash Loss (#200/75um)	8	5.1		0-6
Total Moisture	5	3.5		