



Basic Quality Statistical Summary Report

Period 01/01/2011 - 11/01/2011
Plant 468-Ottawa Lake 58-003
Product 2006-MDOT 6AA
Specification MDOT 6 AA Production

Sieve/Test	Tests	Average	Target	Specification
1 1/2" (37.5mm)	641	100.0		100-100
1" (25mm)	641	99.9		95-100
3/4" (19mm)	641	85.1		
1/2" (12.5mm)	641	40.6		30-60
3/8" (9.5mm)	641	16.0		
#4 (4.75mm)	641	4.0		0-8
#8 (2.36mm)	641	2.5		
Pan	641	0.00		
FM	641	6.92		
Grad Loss	3	0.000		
Wash Loss (#200/75um)	639	1.5		0-2
LA Abrasion (B,500)	1	29.2		
Total Moisture	509	2.1		
Unit Wt (Rodded)	1	98.7		
Unit Wt SSD (Rodded)	1	100.5		
Voids (Rodded)	1	40.1		
Coarseness Factor	641	86.1		
Workability Factor	641	2.5		
Absorption	52	1.88		
SPGR (Dry,Gsb)	52	2.645		
SPGR (SSD)	52	2.695		
SPGR (Apparent,Gsa)	52	2.784		
Chert	66	0.0		
Shale	66	0.1		