



Basic Quality Statistical Summary Report

Period 01/01/2011 - 11/01/2011
Plant 468-Ottawa Lake 58-003
Product 2066-MDOT 6AAA
Specification MIDOT 6 AAA Production

Sieve/Test	Tests	Average	Target	Specification
1 1/2" (37.5mm)	18	100.0		100-100
1" (25mm)	18	94.1		90-100
3/4" (19mm)	18	78.0		60-85
1/2" (12.5mm)	18	41.6		30-60
3/8" (9.5mm)	18	22.3		
#4 (4.75mm)	18	4.2		0-8
Pan	18	0.0		
FM	18	6.95		
Wash Loss (#200/75um)	18	1.7		0-2
Total Moisture	13	3.1		
Absorption	5	1.83		2.5
SPGR (Dry,Gsb)	5	2.651		
SPGR (SSD)	5	2.699		
SPGR (Apparent,Gsa)	5	2.786		
LA Abrasion (B,500)	1	29.2		
Unit Wt (Rodded)	1	98.7		
Unit Wt SSD (Rodded)	1	100.5		
Voids (Rodded)	1	40.1		
Elongated (3:1)	1	0.0		
Elongated (5:1)	1	0.0		
Flat (3:1)	1	0.0		
Flat (5:1)	1	0.0		
Flat/Elongated (3:1)	1	1.8		
Flat/Elongated (5:1)	1	1.8		
Shale	1	0.0		
Chert	1	0.0		