



# Basic Quality Statistical Summary Report

**Period** 01/01/2011 - 11/01/2011  
**Plant** 468-Ottawa Lake 58-003  
**Product** 2004-OH 4  
**Specification** ODOT 4 Production

Sieve/Test	Tests	Average	Target	Specification
2" (50mm)	24	100.0		100-100
1 1/2" (37.5mm)	24	100.0		90-100
1" (25mm)	24	38.6		20-55
3/4" (19mm)	24	6.9		0-15
1/2" (12.5mm)	24	2.9		
3/8" (9.5mm)	24	2.0		0-5
#4 (4.75mm)	24	1.4		
Pan	24	0.0		
FM	24	7.90		
Wash Loss (#200/75um)	22	0.9		
Total Moisture	15	1.7		
Absorption	3	1.63		
SPGR (Dry,Gsb)	3	2.651		
SPGR (SSD)	3	2.694		
SPGR (Apparent,Gsa)	3	2.771		
LA Abrasion (A,500)	1	31.5		
Unit Wt (Rodded)	1	93.7		
Unit Wt SSD (Rodded)	1	95.2		
Voids (Rodded)	1	43.3		