



Basic Quality Statistical Summary Report

Period 01/01/2011 - 11/01/2011
Plant 468-Ottawa Lake 58-003
Product 2067-OH 467
Specification OHDOT 467 Production

Sieve/Test	Tests	Average	Target	Specification
2" (50mm)	57	100.0		100-100
1 1/2" (37.5mm)	57	100.0		95-100
1" (25mm)	57	73.4		
3/4" (19mm)	57	47.4		35-70
1/2" (12.5mm)	57	26.4		
3/8" (9.5mm)	57	14.8		10-30
#4 (4.75mm)	57	3.5		0-5
#200 (75um)	4	2.8		
Pan	57	0.0		
FM	57	7.34		
Wash Loss (#200/75um)	56	1.7		
Total Moisture	42	2.0		
Absorption	15	1.78		
SPGR (Dry,Gsb)	15	2.644		
SPGR (SSD)	15	2.691		
SPGR (Apparent,Gsa)	15	2.775		
LA Abrasion (A,500)	1	31.6		
Unit Wt (Rodded)	1	101.3		
Unit Wt SSD (Rodded)	1	103.1		
Voids (Rodded)	1	38.6		
Chert	9	0.0		
Shale	9	0.1		