



Basic Quality Statistical Summary Report

Period 01/01/2011 - 11/01/2011
Plant 468-Ottawa Lake 58-003
Product 2008-OH 8
Specification ODOT 8 Production

Sieve/Test	Tests	Average	Target	Specification
1/2" (12.5mm)	39	100.0		100-100
3/8" (9.5mm)	39	96.3		85-100
#4 (4.75mm)	39	13.7		10-30
#8 (2.36mm)	39	5.0		0-10
#16 (1.18mm)	39	3.5		0-5
#200 (75um)	6	2.9		
Pan	39	0.0		
FM	39	5.82		
Wash Loss (#200/75um)	38	2.5		
Total Moisture	29	3.2		
Coarseness Factor	39	3.8		
Workability Factor	39	5.0		
Absorption	4	2.43		
SPGR (Dry,Gsb)	4	2.621		
SPGR (SSD)	4	2.684		
SPGR (Apparent,Gsa)	4	2.799		
LA Abrasion (C,500)	1	29.0		
Unit Wt (Rodded)	1	91.9		
Unit Wt SSD (Rodded)	1	94.1		
Voids (Rodded)	1	43.7		
Elongated (3:1)	1	0.0		
Elongated (5:1)	1	0.0		
Flat (3:1)	1	0.0		
Flat (5:1)	1	0.0		
Flat/Elongated (3:1)	1	4.0		
Flat/Elongated (5:1)	1	0.5		