



## Basic Quality Statistical Summary Report

**Period** 01/01/2011 - 11/01/2011  
**Plant** 468-Ottawa Lake 58-003  
**Product** 2109-OH 9 WASHED  
**Specification** OHDOT 9 Production

Sieve/Test	Tests	Average	Target	Specification
3/8" (9.5mm)	88	100.0		95-100
1/4" (6.3mm)	88	86.9		
#4 (4.75mm)	88	44.8		
#8 (2.36mm)	88	2.9		
#16 (1.18mm)	88	1.7		
#30 (0.6mm)	88	1.4		
#50 (0.3mm)	88	1.3		
#100 (0.15mm)	88	1.2		
#200 (75um)	88	1.1		
Pan	88	0.0		
FM	88	5.47		
Wash Loss (#200/75um)	86	1.0		0-3
Total Moisture	42	4.7		
Coarseness Factor	88	0.0		
Workability Factor	88	2.9		
Absorption	12	2.42		
SPGR (Dry,Gsb)	12	2.633		
SPGR (SSD)	12	2.697		
SPGR (Apparent,Gsa)	12	2.813		
LA Abrasion (D,500)	1	31.4		
Unit Wt (Rodded)	1	95.4		
Unit Wt SSD (Rodded)	1	97.8		
Voids (Rodded)	1	41.6		
Shale	30	0.4		
Chert	30	0.0		