



## Basic Quality Statistical Summary Report

**Plant** 468-Ottawa Lake 58-003  
**Product** 2072-Washed Mfg. sand  
**Specification** Washed Mfg. sand

Sieve/Test	Tests	Average	Target	Specification
3/8" (9.5mm)	3	100.0		
#4 (4.75mm)	3	98.1		
#8 (2.36mm)	3	57.4		
#16 (1.18mm)	3	30.7		
#30 (0.6mm)	3	16.1		
#50 (0.3mm)	3	7.1		
#100 (0.15mm)	3	3.3		
#200 (75um)	3	2.68		
PAN (0um)	3	0.00		
FM	3	3.87		
Total Moisture	1	9.2		
Wash Loss (#200/75um)	3	2.6		0-4