



## Basic Quality Statistical Summary Report

**Period** 01/01/2011 - 11/01/2011  
**Plant** 468-Ottawa Lake 58-003  
**Product** 2126-Wayne County 6AA  
**Specification** Wayne County

Sieve/Test	Tests	Average	Target	Specification
1 1/2" (37.5mm)	184	100.0		100-100
1" (25mm)	184	100.0		95-100
3/4" (19mm)	184	84.3		
1/2" (12.5mm)	184	39.9		30-60
3/8" (9.5mm)	184	15.6		
#4 (4.75mm)	184	4.0		0-8
#8 (2.36mm)	184	2.6		
Pan	184	0.00		
FM	184	6.94		
Grad Loss	184	0.000		
Wash Loss (#200/75um)	184	1.6		0-2
Total Moisture	144	2.1		
Coarseness Factor	3	84.1		
Workability Factor	3	2.6		
Absorption	4	1.76		
SPGR (Dry,Gsb)	4	2.651		
SPGR (SSD)	4	2.698		
SPGR (Apparent,Gsa)	4	2.782		
LA Abrasion (B,500)	1	29.2		
Unit Wt (Rodded)	1	98.7		
Unit Wt SSD (Rodded)	1	100.5		
Voids (Rodded)	1	40.1		
Shale	1	0.0		
Chert	1	0.0		