



## Basic Quality Statistical Summary Report

**Plant** 1485-Zeeb Road Pit  
**Product** 2304-1/2 x 3/8 Crush  
**Specification** 1/2 x 3/8 (Production)

Sieve/Test	Tests	Average	Target	Specification
3/4" (19mm)	9	100.0		
1/2" (12.5mm)	9	92.5		85-100
3/8" (9.5mm)	9	37.8		27-51
#4 (4.75mm)	9	2.1		0-11.5
#8 (2.36mm)	9	1.4		0-11.1
#16 (1.18mm)	9	1.2		0-8.9
#30 (0.6mm)	9	1.0		0-8.8
#50 (0.3mm)	9	0.9		0-7.7
#100 (0.15mm)	9	0.8		0-3.6
#200 (75um)	9	0.65		0-3
PAN (0um)	9	0.00		
<hr/>				
% -#200 (75um)	9	0.7		
Coarseness Factor	4	63.4		
Total Moisture	7	2.20		
Wash Loss (#200/75um)	9	0.6		
Workability Factor	4	1.1		