



# Basic Quality Statistical Summary Report

**Plant** 1485-Zeeb Road Pit 81-077  
**Product** 2238-3/4 x 3/8  
**Specification** 3/4 x 3/8 Production

Sieve/Test	Tests	Average	Target	Specification
1" (25mm)	2	100.0		
3/4" (19mm)	2	100.0		
1/2" (12.5mm)	2	66.4		
3/8" (9.5mm)	2	17.6		
#4 (4.75mm)	2	3.7		
#8 (2.36mm)	2	2.2		
#16 (1.18mm)	2			
#30 (0.6mm)	2			
#50 (0.3mm)	2			
#100 (0.15mm)	2			
#200 (75um)	2			
PAN (0um)	2	0.00		
Absorption	1	1.1		
Coarseness Factor	1	89.7		
FM	2	6.8		
LA Abrasion Small (B,500)	1	18.8		
SPGR (Apparent,Gsa)	1	2.748		
SPGR (Dry,Gsb)	1	2.666		
SPGR (SSD)	1	2.696		
Unit Wt (Rodded)	1	103.6		
Unit Wt SSD (Rodded)	1	105		
Voids (Rodded)	1	37.6		
Wash Loss (#200/75um)	2	1.0		
Workability Factor	1	2.2		